

26 May 2014

To whom it may concern:

We hereby confirm that the Silicone used to manufacture the Pipetite range of products conforms to FDA 21 CFR 177.2600. This conformance has been independently verified through test results on the polymer.

Yours faithfully

Andrew Haynes

Director



Our Ref: 84748

22 May 2014

Lake Products Ltd PO Box 100 471 North Shore Mail Centre AUCKLAND

Attention: Mike Sumner

Dear Mike

## Re: Testing Silicone Rubber Component to FDA Food Simulation Test "21 CFR 177.2600"

A silicone rubber component labelled "Pipetite Flat" was received at this laboratory on 19/05/14 for analysis.

We have been asked to test the components against the specifications outlined in the FDA Food Simulation Test "21 CFR 177.2600".

Portions of the component were taken and the surface area was measured. Separate portions were extracted under reflux using the two solvents as dictated – n-hexane and distilled water. The first extraction time was 7 hours, whereby the total extractives were determined. The same portions were subsequently extracted for a further 2 hours and the total extractives determined again.

Our results are as follows:

## **Extraction Solvent: Distilled Water**

Result Specification

Total extractives (initial 7 hours) 0.50 mg/square inch 20 max.

Total extractives (subsequent 2 hours) 0.09 mg/square inch 1 max

Extraction Solvent: n-hexane

Result Specification

Total extractives (initial 7 hours) 17 mg/square inch 175 max.

Total extractives (subsequent 2 hours) 1.1 mg/square inch 4 max

Given the above results, the samples comply with "FDA 21 CFR 177.2600".

Yours faithfully

FLINDERS COOK (TECHNICAL SERVICES) LTD

Owen Bleaken M. Sc. (Hons.)

37 Spring Street, Freemans Bay, Auckland 1011 - PO Box 437, Shortland Street, Auckland 1140, New Zealand Phone: (09) 360 2077 - Mobile: 021 949 194 - Fax: (09) 360 0983 - Email: office@flinderscook.co.nz Website: www.flinderscook.co.nz